

SPECIFICATION FOR SEAMLESS FERRITIC ALLOY-STEEL PIPE FOR HIGH-TEMPERATURE SERVICE



SA-335/SA-335M

(Identical with ASTM Specification A 335/A 335M-99 except for the addition of a maximum hardness requirements of 250 HB for Grades P91 and P92 in 9.3. In 9.4, reference has been made to Grade P92 in two locations under the heading Direction of Test. The headings for Tables 3 and 4 have been corrected such that all three Grades P91, P92, and P122 have been included. In 5.3.4, reference to Grade T92 has been changed editorially to P92. In 13.2 on hardness test requirements, reference to P91 and P92 has been made.)

1. Scope

1.1 This specification covers nominal (average) wall seamless alloy-steel pipe intended for high-temperature service. Pipe ordered to this specification shall be suitable for bending, flanging (vanstoning), and similar forming operations, and for fusion welding. Selection will depend upon design, service conditions, mechanical properties, and high-temperature characteristics.

1.2 Several grades of ferritic steels (Note 1) are covered. Their compositions are given in Table 1.

NOTE 1 — Ferritic steels in this specification are defined as low- and intermediate-alloy steels containing up to and including 10% chromium.

1.3 Supplementary requirements (S1 to S7) of an optional nature are provided. These supplementary requirements call for additional tests to be made, and when desired, shall be so stated in the order together with the number of such tests required.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

NOTE 2 — The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

2. Referenced Documents

2.1 ASTM Standards:

- A 450/A 450M Specification for General Requirements for Carbon Ferritic Alloy, and Austenitic Alloy Steel Tube
- A 530/A 530M Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe
- E 213 Practice for Ultrasonic Examination of Metal Pipe and Tubing
- E 309 Practice for Eddy-Current Examination of Steel Tubular Products Using Magnetic Saturation
- E 381 Method of Macroetch Testing, Inspection, and Rating Steel Products, Comprising Bars, Billets, Blooms, and Forgings
- E 527 Practice for Numbering Alloys and Metals (UNS)
- E 570 Practice for Flux Leakage Examination of Ferromagnetic Steel Tubular Products

2.2 Other Documents:

- SNT-TC-1A Recommended Practice for Nondestructive Personnel Qualification and Certification
- SAE J 1086 Practice for Numbering Metals and Alloys (UNS)

3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

- 3.1.1** Quantity (feet, centimeters, or number of lengths),
- 3.1.2** Name of material (seamless alloy steel pipe),
- 3.1.3** Grade (Table 1),

3.1.4 Manufacture (hot-finished or cold-drawn),

3.1.5 Size (NPS or outside diameter and schedule number or average wall thickness),

3.1.6 Length (specific or random),

3.1.7 End finish (Ends Section of Specification A 530/A 530M),

3.1.8 Optional requirements (Sections 8, 11, and 12, of this specification. See the Sections on Hydrostatic Test Requirements and Permissible Variation in Weight for Seamless Pipe in Specification A 530/A 530M),

3.1.9 Test report required (Certification section of Specification A 530/A 530M),

3.1.10 Specification designation, and

3.1.11 Special requirements or any supplementary requirements selected, or both.

4. General Requirements

4.1 Material furnished to this specification shall conform to the applicable requirements of the current edition of Specification A 530/A 530M, unless otherwise provided herein.

5. Materials and Manufacture

5.1 Pipe may be either hot finished or cold drawn with the finishing treatment as required in 5.3.

5.2 *Grade P2 and P12* — The steel shall be made by coarse-grain melting practice. Specific limits, if any, on grain size or deoxidation practice shall be a matter of agreement between the manufacturer and purchaser.

5.3 Heat Treatment:

5.3.1 All pipe of grades shown in Table 1 except P5c, P91, P92, and P122 as provided in 5.3.2, shall be reheated and furnished in the full-annealed, isothermal annealed, or normalized and tempered condition. If furnished in the normalized and tempered condition, the minimum tempering temperature for Grades P5, P5b, P9, P21, and P22 shall be 1250°F [675°C], the minimum tempering temperature for Grades P1, P2, P11, P12, and P15 shall be 1200°F [650°C].

NOTE 3 — It is recommended that the temperature for tempering should be at least 100°F [50°C] above the intended service temperature; consequently, the purchaser should advise the manufacturer if the service temperature is to be over 1100°F [600°C].

5.3.2 Pipe of Grades P1, P2, and P12, either hot finished or cold drawn, may be given a final heat treatment at 1200°F [650°C] to 1300°F [705°C] instead of heat treatments specified in 5.3.1.

5.3.3 All pipe of Grades P5c shall be given a final heat treatment in the range from 1325°F [715°C] to 1375°F [745°C].

NOTE 4 — Certain of the ferritic steels covered by this specification will harden if cooled rapidly from above their critical temperature. Some will air harden, that is, become hardened to an undesirable degree when cooled in air from high temperatures. Therefore, operations involving heating such steels above their critical temperatures, such as welding, flanging, and hot bending, should be followed by suitable heat treatment.

5.3.4 Grade P92 shall be normalized at 1900°F [1040°C] minimum and tempered at 1350°F [730°C] minimum as a final heat treatment.

5.3.5 Grade P122 shall be normalized at 1900°F [1040°C] minimum, and tempered at 1350°F [730°C] minimum as a final heat treatment.

5.4 Except when Supplementary Requirement S7 is specified by the purchaser, Grade P91 shall be normalized at 1900°F [1040°C] minimum, and tempered at 1350°F [730°C] minimum as a final heat treatment. Alternatively, liquid quenching and tempering is allowed for thicknesses above 3 in. when mutually agreed upon between the manufacturer and the purchaser. In this case the pipe shall be quenched from 1900°F [1040°C] minimum and tempered at 1350°F [730°C] minimum as final heat treatment.

6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 1.

7. Workmanship, Finish, and Appearance

7.1 The pipe manufacturer shall explore a sufficient number of visual surface imperfections to provide reasonable assurance that they have been properly evaluated with respect to depth. Exploration of all surface imperfections is not required but may be necessary to ensure compliance with 7.2.

7.2 Surface imperfections that penetrate more than 12½% of the nominal wall thickness or encroach on the minimum wall thickness shall be considered defects. Pipe with such defects shall be given one of the following dispositions:

7.2.1 The defect may be removed by grinding provided that the remaining wall thickness is within specified limits.

7.2.2 Repaired in accordance with the repair welding provisions of 7.6.

7.2.3 The section of pipe containing the defect may be cut off within the limits of requirements on length.

7.2.4 Rejected.

7.3 To provide a workmanlike finish and basis for evaluating conformance with 7.2, the pipe manufacturer shall remove by grinding the following:

7.3.1 Mechanical marks, abrasions (Note 5) and pits, any of which imperfections are deeper than $\frac{1}{16}$ in. [1.6 mm].

NOTE 5 — Marks and abrasions are defined as cable marks, dings, guide marks, roll marks, ball scratches, scores, die marks, and the like.

7.3.2 Visual imperfections, commonly referred to as scabs, seams, laps, tears, or slivers, found by exploration in accordance with 7.1 to be deeper than 5% of the nominal wall thickness.

7.4 At the purchaser's discretion, pipe shall be subject to rejection if surface imperfections acceptable under 7.2 are not scattered, but appear over a large area in excess of what is considered a workmanlike finish. Disposition of such pipe shall be a matter of agreement between the manufacturer and the purchaser.

7.5 When imperfections or defects are removed by grinding, a smooth curved surface shall be maintained, and the wall thickness shall not be decreased below that permitted by this specification. The outside diameter at the point of grinding may be reduced by the amount so removed.

7.5.1 Wall thickness measurements shall be made with a mechanical caliper or with a properly calibrated nondestructive testing device of appropriate accuracy. In case of dispute, the measurement determined by use of the mechanical caliper shall govern.

7.6 Weld repair shall be permitted only subject to the approval of the purchaser and in accordance with Specification A 530/A 530M.

7.7 The finished pipe shall be reasonably straight.

8. Product Analysis

8.1 At the request of the purchaser, an analysis of two pipes from each lot shall be made by the manufacturer. A lot (Note 6) of pipe shall consist of the following:

<u>NPS Designator</u>	
Under 2	400 or fraction thereof
2 to 5	200 or fraction thereof
6 and over	100 or fraction thereof

NOTE 6 — A lot shall consist of the number of lengths specified in 8.1 of the same size and wall thickness from any one heat of steel.

8.2 The results of these analyses shall be reported to the purchaser or the purchaser's representative, and shall conform to the requirements specified in Table 1.

8.3 For grade P91 the carbon content may vary for the product analysis by -0.01% and $+0.02\%$ from the specified range as per Table 1.

8.4 If the analysis of one of the tests specified in 8.1 does not conform to the requirements specified in 6.1, an analysis of each billet or pipe from the same heat or lot may be made, and all billets or pipe conforming to the requirements shall be accepted.

9. Tensile and Hardness Requirements

9.1 The tensile properties of the material shall conform to the requirements prescribed in Table 2.

9.2 Table 3 list elongation requirements.

9.3 Pipe of Grades P91, P92, and P122 shall have a hardness not exceeding 250 HB/265 HV [25 HRC].

9.4 Table 4 gives the computed minimum elongation values for each $\frac{1}{32}$ in. [0.8 mm] decrease in wall thickness. Where the wall thickness lies between two values above, the minimum elongation value is determined by the following formula:

<u>Direction of Test</u>	<u>Equation</u>
Longitudinal, all grades except P91, P92, and P122	$E = 48t + 15.00$ [$E = 1.87t + 15.00$]
Transverse, except Grades P91, P92, and P122	$E = 32t + 10.00$ [$E = 1.25t + 10.00$]
Longitudinal, P91, P92, and P122	$E = 32t + 10.00$ [$E = 1.25t + 10.00$]

where

E = elongation in 2 in. or 50 mm, % and
 t = actual thickness of specimens, in. [mm]

10. Permissible Variations in Diameter

10.1 Variations in outside diameter shall not exceed those specified in Table 5.

11. Hydrostatic Test

11.1 Each length of pipe shall be subjected to the hydrostatic test, except as provided for in 11.2 or 11.3.

11.2 Unless otherwise specified in the purchase order, each length of pipe shall, at the option of the manufacturer, be subjected to the nondestructive electric test as shown in Section 12 in lieu of the hydrostatic test.

11.3 When specified by the purchaser, pipe shall be furnished without hydrostatic test and without nondestructive examination.

11.4 When specified by the purchaser, pipe shall be furnished with both the hydrostatic test and a nondestructive examination having been performed.

12. Nondestructive Examination

12.1 When selected by the manufacturer or when specified in the order, as an alternative to the hydrostatic test (11.2), or when specified in the purchase order in addition to the hydrostatic test (11.4), each pipe shall be examined by a nondestructive examination method in accordance with Practice E 213, Practice E 309, or Practice E 570. The range of pipe sizes that may be examined by each method shall be subject to the limitations in the scope of the respective practices.

12.2 The following information is for the benefit of the user of this specification:

12.2.1 The reference standards defined in 12.8 are convenient standards for standardization of nondestructive examination equipment. The dimensions of these standards should not be construed as the minimum size imperfection detectable by such equipment.

12.2.2 Ultrasonic examination can be performed to detect both longitudinally and transversely oriented discontinuities. It should be recognized that different techniques should be employed to detect differently oriented imperfections. The examination may not detect short, deep imperfections.

12.2.3 The eddy current examination referenced in this specification has the capability to detect significant discontinuities, especially of the short, abrupt type.

12.2.4 The flux leakage examination referred to in this specification is capable of detecting the presence and location of significant longitudinally or transversely oriented discontinuities. It should be recognized that different techniques should be employed to detect differently oriented imperfections.

12.2.5 The hydrostatic test of Section 11 has the capability to find imperfections of a size that permit the test fluid to leak through the pipe wall so that it may be either visually seen or detected by a loss of fluid pressure. This test may not detect very tight, through-wall imperfections, or imperfections that extend into the wall without complete penetration.

12.2.6 A purchaser interested in ascertaining the nature (type, size, location, and orientation) of discontinuities that can be detected in the specific application of these examinations should discuss this with the manufacturer of the tubular products.

12.3 *Time of Examination* — Nondestructive examination for specification acceptance shall be performed after

all mechanical processing, heat treatments, and straightening operations. This requirement does not preclude additional testing at earlier stages in the processing.

12.4 *Surface Conditions:*

12.4.1 All surfaces shall be clean and free of scale, dirt, grease, paint, or other foreign material that could interfere with interpretation of test results. The methods used for cleaning and preparing the surfaces for examination shall not be detrimental to the base metal or the surface finish.

12.4.2 Excessive surface roughness or deep scratches can produce signals that interfere with the test (see 12.10.2.3).

12.5 *Extent of Examination:*

12.5.1 The relative motion of the pipe and the transducer(s), coil(s), or sensor(s) shall be such that the entire pipe surface is scanned, except for end effects as noted in 12.5.2.

12.5.2 The existence of end effects is recognized, and the extent of such effects shall be determined by the manufacturer, and, if requested, shall be reported to the purchaser. Other nondestructive tests may be applied to the end areas, subject to agreement between the purchaser and the manufacturer.

12.6 *Operator Qualifications* — The test unit operator shall be certified in accordance with SNT-TC-1A, or an equivalent, recognized, and documented standard.

12.7 *Test Conditions:*

12.7.1 For examination by the ultrasonic method, the minimum nominal transducer frequency shall be 2.25 MHz.

12.7.2 For eddy current testing, the excitation coil frequency shall be 10 kHz, or less.

12.8 *Reference Standards:*

12.8.1 Reference standards of convenient length shall be prepared from a length of pipe of the same grade, size (NPS or outside diameter and schedule or wall thickness), surface finish, and heat treatment condition as the pipe to be examined.

12.8.2 For ultrasonic testing, the reference notches shall be any one of the three common notch shapes shown in Practice E 213, at the option of the manufacturer. The depth of the notch shall not exceed $12\frac{1}{2}\%$ of the specified nominal wall thickness of the pipe or 0.004 in. [0.1 mm], whichever is greater. The length of the notch shall be at least twice the diameter of the transducer(s). The width of the notch shall not exceed the depth.

12.8.3 For eddy current testing, the reference standard shall contain, at the option of the manufacturer, any one of the following discontinuities:

12.8.3.1 Drilled Hole — The reference standard shall contain three or more holes, equally spaced circumferentially around the pipe and longitudinally separated by a sufficient distance to allow distinct identification of the signal from each hole. The holes shall be drilled radially and completely through the pipe wall, with care being taken to avoid distortion of the pipe while drilling. The hole diameter shall vary with NPS as follows:

<u>NPS Designator</u>	<u>Hole Diameter</u>
$\frac{1}{2}$	0.039 in. [1 mm]
above $\frac{1}{2}$ to $1\frac{1}{4}$	0.055 in. [1.4 mm]
above $1\frac{1}{4}$ to 2	0.071 in. [1.8 mm]
above 2 to 5	0.087 in. [2.2 mm]
above 5	0.106 in. [2.7 mm]

12.8.3.2 Transverse Tangential Notch — Using a round tool or file with a $\frac{1}{4}$ in. [6.4 mm] diameter, a notch shall be filed or milled tangential to the surface and transverse to the longitudinal axis of the pipe. Said notch shall have a depth not exceeding 12½% of the specified nominal wall thickness of the pipe or 0.004 in. [0.1 mm], whichever is greater.

12.8.3.3 Longitudinal Notch — A notch 0.031 in. or less in width shall be machined in a radial plane parallel to the tube axis on the outside surface of the pipe, to have a depth not exceeding 12½% of the specified nominal wall thickness of the pipe or 0.004 in. [0.1 mm], whichever is greater. The length of the notch shall be compatible with the testing method.

12.8.4 For flux leakage testing, the longitudinal reference notches shall be straight-sided notches machined in a radial plane parallel to the pipe axis. For wall thickness less than $\frac{1}{2}$ in. [12.7 mm], outside and inside notches shall be used; for wall thicknesses equal to or greater than $\frac{1}{2}$ in., only an outside notch shall be used. Notch depth shall not exceed 12½% of the specified nominal wall thickness or 0.004 in. [0.1 mm], whichever is greater. Notch length shall not exceed 1 in. [25.4 mm], and the width shall not exceed the depth. Outside and inside notches shall have sufficient separation to allow distinct identification of the signal from each notch.

12.8.5 More or smaller reference discontinuities, or both, may be used by agreement between the purchaser and the manufacturer.

12.9 Standardization Procedure:

12.9.1 The test apparatus shall be standardized at the beginning and end of each series of pipes of the same size (NPS or diameter and schedule or wall thickness),

grade and heat treatment condition, and at intervals not exceeding 4 h during the examination of such pipe. More frequent standardizations may be performed at the manufacturer's option or may be required upon agreement between the purchaser and the manufacturer.

12.9.2 The test apparatus shall also be standardized after any change in test system settings, change of operator, equipment repair, or interruption due to power loss, shutdown, or operator breaks.

12.9.3 The reference standard shall be passed through the test apparatus at same speed and test system settings as the pipe to be tested.

12.9.4 The signal-to-noise ratio for the reference standard shall be 2.5 to 1 or greater and the reference signal amplitude for each discontinuity shall be at least 50% of full scale of the display.

12.9.5 If upon any standardization the reference signal amplitude has decreased by 25% (2 db), the test apparatus shall be considered out of standardization. The test system settings may be changed, or the transducer(s), coil(s), or sensor(s) adjusted, and the unit restandardized, but all pipe tested since the last acceptable standardization must be retested.

12.10 Evaluation of Imperfections:

12.10.1 Pipes producing a signal equal to or greater than the signal produced by the reference standard shall be positively identified and they shall be separated from the acceptable pipes. The area producing the signal may be reexamined.

12.10.2 Such pipes shall be subject to one of the following three dispositions:

12.10.2.1 The pipes may be rejected without further examination, at the discretion of the manufacturer.

12.10.2.2 The pipes shall be rejected, but may be repaired, if the test signal was produced by imperfections which cannot be identified, or was produced by cracks or crack-like imperfections. These pipes may be repaired by grinding (in accordance with 7.2.1), welding (in accordance with 7.6), or sectioning (in accordance with 7.2.3). To be accepted, a repaired pipe must pass the same nondestructive examination by which it was rejected, and it must meet the remaining wall thickness requirements of this specification.

12.10.2.3 Such pipes may be evaluated in accordance with the provisions of Section 7, if the test signals were produced by visual imperfections such as those listed below:

- (a) Scratches,
- (b) Surface roughness,
- (c) Dings,

- (d) Straightener marks,
- (e) Cutting chips,
- (f) Steel die stamps,
- (g) Stop marks, or
- (h) Pipe reducer ripple.

13. Mechanical Tests Required

13.1 Transverse or Longitudinal Tension Test and Flattening Test, Hardness Test, or Bend Test — For material heat treated in a batch-type furnace, tests shall be made on 5% of the pipe from each treated lot (Note 7). For small lots, at least 1 pipe shall be tested. For material heat treated by the continuous process, tests shall be made on a sufficient number of pipe to constitute 5% of the lot (Note 7), but in no case less than 2 pipe.

NOTE 7 — The term “lot” applies to all pipe of the same nominal size and wall thickness (or schedule) which is produced from the same heat of steel and subjected to the same finishing treatment in a continuous furnace; when final heat treatment is in a batch-type furnace, the lot shall include only that pipe which is heat treated in the same furnace charge.

13.2 Hardness Test:

13.2.1 For pipe of Grades P91, P92, and P122, Brinell, Vickers, or Rockwell hardness tests shall be made on a specimen from each lot (see Note 7).

13.3 Bend Test:

13.3.1 For pipe whose diameter exceeds NPS 25 and whose diameter to wall thickness ratio is 7.0 or less shall be subjected to the bend test instead of the flattening test. Other pipe whose diameter equals or exceeds NPS 10 may be given the bend test in place of the flattening test subject to the approval of the purchaser.

13.3.2 The bend test specimens shall be bent at room temperature through 180°F without cracking on the outside of the bent portion. The inside diameter of the bend shall be 1 in. [25 mm].

13.3.3 Test specimens for the bend test specified in 13.3 shall be cut from one end of the pipe and, unless otherwise specified, shall be taken in a transverse direction. One test specimen shall be taken as close to the outer surface as possible and another from as close to the inner surface as possible. The specimens shall be either $\frac{1}{2}$ by $\frac{1}{2}$ in. [12.5 by 12.5 mm] in section or 1 by $\frac{1}{2}$ in. [25 by 12.5 mm] in section with the corners rounded to a radius not over $\frac{1}{16}$ in. [1.6 mm] and need not exceed 6 in. [150 mm] in length. The side of the samples placed in tension during the bend shall be the side closest to the inner and outer surface of the pipe, respectively.

14. Certification

14.1 In addition to the information required by Specification A 530/A 530M, the certification shall state

whether or not the material was hydrostatically tested. If the material was nondestructively examined, the certification shall so state and shall show which practice was followed and what reference discontinuities were used. In addition, the test method information as given in Table 3 shall be appended to the specification number and grade shown on the certification.

15. Product Marking

15.1 In addition to the marking prescribed in Specification A 530/A 530M, the marking shall include the length, an additional symbol “S,” if the pipe conforms to any of the Supplementary Requirements S1 to S6, the ANSI schedule number, and the heat number or manufacturer’s number by which the heat can be identified. Furthermore, the marking designated in Table 6 to indicate the test method(s) shall be included. Marking may be by stenciling, stamping, or rolling. Pipe that has been weld repaired in accordance with 7.6 shall be marked “WR.”

16. Government Procurement

16.1 Scale-Free Pipe:

16.1.1 When specified in the contract or order, the following requirements shall be considered in the inquiry contract or order for agencies of the U.S. Government where scale-free pipe or tube is required. These requirements shall take precedence if there is a conflict between these requirements and the product specification.

16.1.2 The requirements of Specification A 530/A 530M for pipe and Specification A 450/A 450M for tubes shall be applicable when pipe or tube is ordered to this specification.

16.1.3 Pipe and tube shall be one of the following grades as specified herein:

Grade	UNS Designation
P11	K11597
P22	K21590
P5	K41545

16.1.4 Part Number:

16.1.4.1 Pipe shall be ordered to nominal pipe size and schedule specified in ANSI B36.10.

Example: A 335/A 335M Pipe P-11 NPS 12 Sch 40

Specification Number	ASTM A 335/A 335M
Pipe	P
Grade	P-11
NPS	12
Wall	0.375

16.1.4.2

Specification Number	ASTM A 335/A 335M
Tube	T
Grade	P-11
Outside Diameter	0.250
Wall	0.035

16.1.5 Ordering Information — Orders for material under this specification shall include the following in addition to the requirements of Section 4:

16.1.5.1 Pipe or tube,

16.1.5.2 Part number,

16.1.5.3 Ultrasonic inspection, if required,

16.1.5.4 If shear wave test is to be conducted in two opposite circumferential directions, and

16.1.5.5 Level of preservation and packing required.

17. Keywords

17.1 alloy steel pipe; high-temperature service; seamless steel pipe; steel pipe; temperature service applications, high

TABLE 1
CHEMICAL REQUIREMENTS

Grade	UNS Designation ^A	Composition, %							
		Carbon	Manganese	Phosphorus, Max.	Sulfur, Max.	Silicon	Chromium	Molybdenum	Others
P1	K11522	0.10–0.20	0.30–0.80	0.025	0.025	0.10–0.50	...	0.44–0.65	...
P2	K11547	0.10–0.20	0.30–0.61	0.025	0.025	0.10–0.30	0.50–0.81	0.44–0.65	...
P5	K41545	0.15 max.	0.30–0.60	0.025	0.025	0.50 max.	4.00–6.00	0.45–0.65	...
P5b	K51545	0.15 max.	0.30–0.60	0.025	0.025	1.00–2.00	4.00–6.00	0.45–0.65	...
P5c	K41245	0.12 max.	0.30–0.60	0.025	0.025	0.50 max.	4.00–6.00	0.45–0.65	... ^B
P9	K90941	0.15 max.	0.30–0.60	0.025	0.025	0.25–1.00	8.00–10.00	0.90–1.10	...
P11	K11597	0.05–0.15	0.30–0.60	0.025	0.025	0.50–1.00	1.00–1.50	0.44–0.65	...
P12	K11562	0.05–0.15	0.30–0.61	0.025	0.025	0.50 max.	0.80–1.25	0.44–0.65	...
P15	K11578	0.05–0.15	0.30–0.60	0.025	0.025	1.15–1.65	...	0.44–0.65	...
P21	K31545	0.05–0.15	0.30–0.60	0.025	0.025	0.50 max.	2.65–3.35	0.80–1.06	...
P22	K21590	0.05–0.15	0.30–0.60	0.025	0.025	0.50 max.	1.90–2.60	0.87–1.13	...
P91	K90901	0.08–0.12	0.30–0.60	0.020	0.010	0.20–0.50	8.00–9.50	0.85–1.05	V 0.18–0.25 N 0.030–0.070 Ni 0.40 max. Al 0.04 max. Cb 0.06–0.10
P92	K92460	0.07–0.13	0.30–0.60	0.020	0.010	0.50 max.	8.50–9.50	0.30–0.60	V 0.15–0.25 N 0.03–0.07 Ni 0.40 max. Al 0.04 max. Cb 0.04–0.09 W 1.5–2.00 B 0.001–0.006
P122	K92930	0.07–0.14	0.70 max.	0.020	0.010	0.50 max.	10.00–12.50	0.25–0.60	V 0.15–0.30 W 1.50–2.50 Cu 0.30–1.70 Cb 0.04–0.10 B 0.0005–0.005 N 0.040–0.100 Ni 0.50 max. Al 0.040 max.

NOTES:

^A New designation established in accordance with Practice E 527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

^B Grade P5c shall have a titanium content of not less than 4 times the carbon content and not more than 0.70%; or a columbium content of 8 to 10 times the carbon content.

TABLE 2
TENSILE REQUIREMENTS

Identification Symbol	P1, P2	P12	P91	P92	P122	All Others
Tensile Strength, min.:						
ksi	55	60	85	90	90	60
MPa	380	415	585	620	620	415
Yield strength, min.:						
ksi	30	32	60	64	58	30
MPa	205	220	415	440	440	205

TABLE 3
ELONGATION REQUIREMENTS

	Elongation Requirements, All Grades Except P91, P92, and P122		Elongation Requirements, Grades P91, P92, and P122	
	Longitudinal	Transverse	Longitudinal	Transverse
Elongation in 2 in. or 50 mm (or 4D), min., %:				
Basic minimum elongation for wall $\frac{5}{16}$ in. [8 mm] and over in thickness, strip tests, and for all small sizes tested in full section	30	20	20	...
When standard round 2-in. or 50-mm gage length or proportionally smaller size specimen with the gage length equal to 4D (4 times the diameter) is used	22	14	20	13
For strip tests a deduction for each $\frac{1}{32}$ in. [0.8 mm] decrease in wall thickness below $\frac{5}{16}$ in. [8 mm] from the basic minimum elongation of the following percentage points shall be made	1.50 ^A	1.00 ^A	1.00 ^A	...

NOTE

^A Table 4 gives the calculated minimum values.

TABLE 4
COMPUTED MINIMUM ELONGATION VALUES

Wall Thickness		Elongation in 2 in. or 50 mm, min., %		
		All Grades Except P91, P92, and P122		Grades P91, P92, and P122
in.	mm	Longitudinal	Transverse	Longitudinal
$\frac{5}{16}$ (0.312)	8	30	20.0	20
$\frac{9}{32}$ (0.281)	7.2	29	19.0	19
$\frac{1}{4}$ (0.250)	6.4	27	18.0	18
$\frac{7}{32}$ (0.219)	5.6	26	...	17
$\frac{3}{16}$ (0.188)	4.8	24	...	16
$\frac{5}{32}$ (0.156)	4	22	...	15
$\frac{1}{8}$ (0.125)	3.2	21	...	14
$\frac{3}{32}$ (0.094)	2.4	20	...	13
$\frac{1}{16}$ (0.062)	1.6	18	...	12

TABLE 5
VARIATIONS IN OUTSIDE DIAMETER PERMISSIBLE
VARIATIONS IN OUTSIDE DIAMETER

NPS Designator	Over		Under	
	in.	mm	in.	mm
$\frac{1}{8}$ to $1\frac{1}{2}$, incl.	$\frac{1}{64}$ (0.015)	0.40	$\frac{1}{64}$ (0.015)	0.40
Over $1\frac{1}{2}$ to 4, incl.	$\frac{1}{32}$ (0.031)	0.79	$\frac{1}{32}$ (0.031)	0.79
Over 4 to 8, incl.	$\frac{1}{16}$ (0.062)	1.59	$\frac{1}{32}$ (0.031)	0.79
Over 8 to 12, incl.	$\frac{3}{32}$ (0.093)	2.38	$\frac{1}{32}$ (0.031)	0.79
Over 12	± 1%			

TABLE 6
TEST METHOD INFORMATION FOR CERTIFICATION
AND MARKING

Hydrostatic	Nondestructive	Marking
YES	NO	Test Pressure
NO	YES	NDE
NO	NO	NH
YES	YES	Test Pressure/NDE

SUPPLEMENTARY REQUIREMENTS

One or more of the following supplementary requirements shall apply only when specified in the purchase order. The purchaser may specify a different frequency of test or analysis than is provided in the supplementary requirement. Subject to agreement between the purchaser and manufacturer, retest and retreatment provisions of these supplementary requirements may also be modified.

S1. Product Analysis

S1.1 Product analysis shall be made on each length of pipe. Individual lengths failing to conform to the chemical composition requirements shall be rejected.

S2. Transverse Tension Tests

S2.1 A transverse tension test shall be made on a specimen from one end or both ends of each pipe NPS 8 and over. If this supplementary requirement is specified, the number of tests per pipe shall also be specified. If a specimen from any length fails to meet the required tensile properties (tensile, yield, and elongation), that length shall be rejected subject to retreatment in accordance with Specification A 530/A 530M and satisfactory retest.

S3. Flattening Test

S3.1 The flattening test of Specification A 530/A 530M shall be made on a specimen from one end or both ends of each pipe. Crop ends may be used. If this supplementary requirement is specified, the number of tests per pipe shall also be specified. If a specimen from any length fails because of lack of ductility prior to satisfactory completion of the first step of the flattening test requirement, that pipe shall be rejected subject to retreatment in accordance with Specification A 530/A 530M and satisfactory retest. If a specimen from any length of pipe fails because of a lack of soundness, that length shall be rejected, unless subsequent retesting indicates that the remaining length is sound. The bend test of 13.2 shall be substituted for the flattening test for pipe whose diameter exceeds NPS 25 and whose diameter to wall thickness ratio is 7.0 or less.

S4. Metal Structure and Etching Tests

S4.1 The steel shall be homogenous as shown by etching tests conducted in accordance with the appropriate portions of Method E 381. Etching tests shall be made on a cross-section from one end or both ends of each pipe and shall show sound and reasonably uniform

material free from injurious laminations, cracks, and similar objectionable defects. If this supplementary requirement is specified, the number of tests per pipe required shall also be specified. If a specimen from any length shows objectionable defects, the length shall be rejected, subject to removal of the defective end and subsequent retests indicating the remainder of the length to be sound and reasonably uniform material.

NOTE S1 — Pending development of etching methods applicable to the product covered by this specification, it is recommended that the Recommended Practice for a Standard Macro Etch Test for Routine Inspection of Iron and Steel, described in the *Metals Handbook*, Am. Soc. for Metals, 1948 edition, p. 389, be followed.

S5. Photomicrographs

S5.1 When requested by the purchaser and so stated in the order, the manufacturer shall furnish one photomicrograph at 100 diameters from a specimen of pipe in the as-finished condition for each individual size and wall thickness from each heat, for pipe NPS 3 and over. Such photomicrographs shall be suitably identified as to pipe size, wall thickness, and heat. No photomicrographs for the individual pieces purchased shall be required except as specified in Supplementary Requirement S6. Such photomicrographs are for information only, to show the actual metal structure of the pipe as finished.

S6. Photomicrographs for Individual Pieces

S6.1 In addition to the photomicrographs required in accordance with Supplementary Requirement S5, the purchaser may specify that photomicrographs shall be furnished from each end of one or more pipes from each lot of pipe NPS 3 and larger in the as-finished condition. The purchaser shall state in the order the number of pipes to be tested from each lot. When photomicrographs are required on each length, the photomicrographs from each lot of pipe in the as-finished condition, which may be required under Supplementary Requirement S5, may be omitted. All photomicrographs required shall be properly identified as to heat number, size, and wall thickness of

pipe from which the section was taken. Photomicrographs shall be further identified to permit association of each photomicrograph with the individual length of pipe it represents.

S7. Alternative Heat Treatment — Grade P91

S7.1 Grade P91 shall be normalized in accordance with 5.3 and tempered at a temperature, to be specified

by the purchaser, less than 1350°F [730°C]. It shall be the purchaser's responsibility to subsequently temper at 1350°F [730°C] minimum. All mechanical tests shall be made on material heat treated in accordance with 5.3. The certification shall reference this supplementary requirement indicating the tempering temperature applied. The notation "S7" shall be included with the required marking of the pipe.